

試驗報告

報告號碼：HB-10-08995X

頁數：1 OF 1

日期：99年12月13日

委託單位：茂系亞股份有限公司
地址：台北市信義區永吉路30巷177弄36號
樣品名稱：日安徽炭化合物板
樣品型號：MF-A-C648
原產地：台灣
送驗人員：茂系亞股份有限公司(饒允政)
收件日期：99年12月03日
試驗日期：99年12月08日~99年12月09日
備註：以上資料由顧客提供(收件及試驗日期除外)

試驗結果：

試驗項目	試驗方法	試驗結果
反覆煮沸浸水剝離	參考 CNS 1349(2008)	1 試驗後，試片各側面同一膠合層無剝離部分之長度達 50 mm 以上
		2 試驗後，試片各側面同一膠合層無剝離部分之長度達 50 mm 以上
		3 試驗後，試片各側面同一膠合層無剝離部分之長度達 50 mm 以上
		4 試驗後，試片各側面同一膠合層無剝離部分之長度達 50 mm 以上

註：沸水溫度約 100°C。

規範要求值僅供參考，合格之判定以委託單位實際要求為準。

游家俊
報告簽署人

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

TEST REPORT

Report No. : HB-10-08995XA

Page : 1 of 1

Date : Dec. 13, 2010

Applicant: MOSIA FLOORING CORP.
 Address: No.36, Aly. 177, Ln. 30, Yongji Rd., Xinyi Dist., Taipei City 110, Taiwan(R.O.C.)
 Sample Name: Daily Secured Healthy Micro-Carbonization Plywood
 Type of Sample: MF-A-C648
 Source area: Taiwan
 Sample Submitted By: MOSIA FLOORING CORP.(JAO YUN CHENG)
 Date of Sample Received: Dec. 03, 2010
 Date of Testing: Dec. 08, 2010~ Dec. 09, 2010
 Remark: The information mentioned in the above section is provided by customer
 (Exclude received and tested date)

We have tested the submitted samples as required and the following results were obtained :

Test Item	Test Method	Test Results	
Repetitive boiling water soaking delaminating test	CNS 1349(2008) Modified	1	Length ok non-delaminated part in the same glue lines of each of specimen after repetitive boiling water soaking delaminating test is more than 50mm
		2	Length ok non-delaminated part in the same glue lines of each of specimen after repetitive boiling water soaking delaminating test is more than 50mm
		3	Length ok non-delaminated part in the same glue lines of each of specimen after repetitive boiling water soaking delaminating test is more than 50mm
		4	Length ok non-delaminated part in the same glue lines of each of specimen after repetitive boiling water soaking delaminating test is more than 50mm

Note: 1.The temperature of boiling water is about 100°C.


2.This is the first additional report of HB-10-08995X, issued on Dec. 13, 2010.

The value of required specifications are for reference only.

Conformity judgment is the Applicant's final verdict.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at www.sgs.com/terms_and_conditions.htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.



Signed for and on behalf of
SGS TAIWAN Ltd.

TWA3421230